



Prime Recycled Pellets & rCompounds for Profile and Pipe Extrusion

Product example	Description	Possible colors	MFR (g/10min)	Density (g/cm ³)
RSH LDPE 2010 F	Regranulate from clean post-industrial raw materials (100% PIR)	black, colored, white, natural	0.5 - 1.0 (190°C / 2.16kg)	0.92 - 0.94
HDPE 5009 E	Regranulate from clean post-industrial raw materials (100% PIR), high pressure pipe content	black	0.5 - 0.9 (190°C / 5kg)	0.955
HDPE 5010 E	Regranulate from clean PIR raw materials (100% PIR), high pressure pipe content, low PP content possible	black	0.5 - 1.0 (190°C / 5kg)	0.955
PPC 1010 E	Regranulate from clean post-industrial raw materials (100% PIR)	black	0.5 - 1.0 (230°C / 2.16kg)	0.940
PPC 1015 E	Regranulate from clean post-industrial raw materials (100% PIR)	black	1.0 - 1.5 (230°C / 2.16kg)	0.940
PPC 1025 E	Regranulate from clean post-industrial raw materials (100% PIR)	black	1.5 - 2.5 (230°C / 2.16kg)	0.940
PPC 0112 MF5	rCompound from clean post-industrial raw materials, mineral reinforced, slightly increased stiffness	grey	0.5 - 1.0 (230°C / 2.16kg)	0.960
PP 0222 MF40	rCompound from clean post-industrial raw materials, mineral reinforced, increased stiffness	black	2 (230°C / 2.16kg)	1.200

This overview shows only a small part of our portfolio with exemplary properties. Please let us know your requirements - we will be pleased to offer you further products from our portfolio or develop individual solutions for your needs. We will be delighted to advise you.

